

Quinn Therm Limited

Scotchtown
Ballyconnell
Co Cavan
Ireland

Tel: 00 353 49 9525600 Fax: 00 353 49 9525601

e-mail: info@quinn-buildingproducts.com

website: www.quinn-buildingproducts.com



Agrément Certificate

07/4444

Product Sheet 4

QUINN THERM

QUINN THERM QR PITCHED ROOF BOARD

This Agrément Certificate Product Sheet⁽¹⁾ relates to Quinn Therm QR Pitched Roof Board, a rigid polyisocyanurate (PIR) foam board with composite foil-facings, for use as insulation installed above, between and/or below rafters in tiled or slated pitched roofs, in horizontal ceilings, dwarf walls and dormer cheeks, in new and existing domestic and non-domestic buildings.

(1) Hereinafter referred to as 'Certificate'.

CERTIFICATION INCLUDES:

- factors relating to compliance with Building Regulations where applicable
- factors relating to additional non-regulatory information where applicable
- independently verified technical specification
- assessment criteria and technical investigations
- design considerations
- installation guidance
- regular surveillance of production
- formal three-yearly review.



KEY FACTORS ASSESSED

Thermal performance — the product has a declared thermal conductivity (λ_D)* of $0.022 \text{ W}\cdot\text{m}^{-1}\cdot\text{K}^{-1}$ (see section 6).

Condensation risk — the product can contribute to limiting the risk of condensation (see section 7).

Behaviour in relation to fire — the product has a reaction to fire classification* to BS EN 13501-1 : 2007 of Class F for 20 mm to 55 mm thicknesses and Class E for 60 mm to 200 mm thicknesses (see section 8).

Resistance to moisture — the product will not be adversely affected by rain showers during installation, nor by wind-driven snow or rain penetrating the tiling in service (see section 11).

Durability — the product is durable, rot-proof and sufficiently stable to remain effective as insulation for the life of the building (see section 13).

The BBA has awarded this Certificate to the company named above for the product described herein. This product has been assessed by the BBA as being fit for its intended use provided it is installed, used and maintained as set out in this Certificate.

On behalf of the British Board of Agrément

John Albon – Head of Approvals
Construction Products

Claire Curtis-Thomas
Chief Executive

Date of Second issue: 6 April 2016

Originally certificated on 18 November 2011

The BBA is a UKAS accredited certification body – Number 113.

The schedule of the current scope of accreditation for product certification is available in pdf format via the UKAS link on the BBA website at www.bbacerts.co.uk

Readers are advised to check the validity and latest issue number of this Agrément Certificate by either referring to the BBA website or contacting the BBA direct.

British Board of Agrément

Bucknalls Lane
Watford
Herts WD25 9BA

©2016

Page 1 of 13

tel: 01923 665300
fax: 01923 665301
clientservices@bba.star.co.uk
www.bbacerts.co.uk

Regulations

In the opinion of the BBA, Quinn Therm QR Pitched Roof Board, if installed, used and maintained in accordance with this Certificate, can satisfy or contribute to satisfying the relevant requirements of the following Building Regulations (the presence of a UK map indicates that the subject is related to the Building Regulations in the region or regions of the UK depicted):



The Building Regulations 2010 (England and Wales) (as amended)

Requirement:	C2(c)	Resistance to moisture
Comment:		The product can contribute to satisfying this Requirement. See sections 7.1 and 7.5 of this Certificate.
Requirement:	L1(a)(i)	Conservation of fuel and power
Comment:		The product can contribute to satisfying this Requirement. See section 6 of this Certificate.
Regulation:	7	Materials and workmanship
Comment:		The product is acceptable. See section 13 and the <i>Installation</i> part of this Certificate.
Requirement:	26	CO₂ emission rates for new buildings
Requirement:	26A	Fabric energy efficiency rates for new dwellings (applicable to England only)
Requirement:	26A	Primary energy consumption rates for new buildings (applicable to Wales only)
Requirement:	26B	Fabric performance values for new dwellings (applicable to Wales only)
Comment:		The product can contribute to satisfying these Regulations. See section 6 of this Certificate.



The Building (Scotland) Regulations 2004 (as amended)

Regulation:	8(1)	Durability, workmanship and fitness of materials
Comment:		The product is acceptable. See section 13 and the <i>Installation</i> part of this Certificate.
Regulation:	9	Building standards applicable to construction
Standard:	3.15	Condensation
Comment:		The product can contribute to satisfying this Standard, with reference to clauses 3.15.1 ⁽¹⁾⁽²⁾ , 3.15.4 ⁽¹⁾ and 3.15.7 ⁽¹⁾⁽²⁾ . See sections 7.1 and 7.6 of this Certificate.
Standard:	6.1(b)	Carbon dioxide emissions
Standard:	6.2	Building insulation envelope
Comment:		The product can contribute to satisfying these Standards, with reference to clauses, or parts of clauses, 6.1.1 ⁽¹⁾ , 6.1.6 ⁽¹⁾ , 6.2.1 ⁽¹⁾⁽²⁾ , 6.2.3 ⁽¹⁾ , 6.2.4 ⁽¹⁾⁽²⁾ , 6.2.5 ⁽²⁾ , 6.2.6 ⁽¹⁾⁽²⁾ , 6.2.7 ⁽¹⁾ , 6.2.8 ⁽²⁾ , 6.2.9 ⁽¹⁾⁽²⁾ , 6.2.10 ⁽¹⁾ , 6.2.11 ⁽¹⁾⁽²⁾ , 6.2.12 ⁽²⁾ and 6.2.13 ⁽¹⁾⁽²⁾ . See section 6 of this Certificate.
Standard:	7.1(a)(b)	Statement of sustainability
Comment:		The product can contribute to satisfying the relevant requirements of Regulation 9, Standards 1 to 6, and therefore will contribute to a construction meeting a bronze level of sustainability as defined in this Standard. In addition, the product can contribute to a construction meeting a higher level of sustainability as defined in this Standard, with reference to clauses 7.1.4 ⁽¹⁾⁽²⁾ [Aspects 1 ⁽¹⁾⁽²⁾ and 2 ⁽¹⁾], 7.1.6 ⁽¹⁾⁽²⁾ [Aspects 1 ⁽¹⁾⁽²⁾ and 2 ⁽¹⁾] and 7.1.7 ⁽¹⁾⁽²⁾ [Aspect 1 ⁽¹⁾⁽²⁾]. See section 6 of this Certificate.
Regulation:	12	Building standards applicable to conversions
Comment:		Comments made in relation to this product under Regulation 9, Standards 1 to 6, also apply to this Regulation, with reference to clause 0.12.1 ⁽¹⁾ and Schedule 6 ⁽¹⁾ .

(1) Technical Handbook (Domestic).

(2) Technical Handbook (Non-Domestic).



The Building Regulations (Northern Ireland) 2012 (as amended)

Regulation:	23	Fitness of materials and workmanship
Comment:		The product is acceptable. See section 13 and the <i>Installation</i> part of this Certificate.
Regulation:	29	Condensation
Comment:		The product can contribute to satisfying this Regulation. See section 7.1 of this Certificate.
Regulation:	39(a)(i)	Conservation measures
Regulation:	40	Target carbon dioxide emission rate
Comment:		The product can contribute to satisfying these Regulations. See section 6 of this Certificate.

Construction (Design and Management) Regulations 2015

Construction (Design and Management) Regulations (Northern Ireland) 2007

Information in this Certificate may assist the client, Principal Designer/CDM co-ordinator, designer and contractors to address their obligations under these Regulations.

See sections: 3 *Delivery and site handling* (3.4) and 14 *General* (14.2) of this Certificate.

Additional Information

NHBC Standards 2016

NHBC accepts the use of Quinn Therm QR Pitched Roof Board, when installed and used in accordance with this Certificate, in relation to *NHBC Standards 2016*, Chapter 7.2 *Pitched roofs*.

CE marking

The Certificate holder has taken the responsibility of CE marking the product in accordance with harmonised European Standard BS EN 13165 : 2012. An asterisk (*) appearing in this Certificate indicates that data shown is given in the manufacturer's Declaration of Performance.

Technical Specification

1 Description

Quinn Therm QR Pitched Roof Board comprises a rigid polyisocyanurate (PIR) board with composite foil-facings, with the nominal characteristics given in Table 1.

Table 1 Nominal characteristics

Length x Width (mm)	2400 x 1200
Thickness ⁽¹⁾ (mm)	20 to 200 (in 5 mm increments)
Edge detail	Plain square edge
Facings	Printed composite foil-facing one side, unprinted composite foil-facing other side.
Compressive stress at 10% deformation* (kPa)	≥ 150

2 Manufacture

2.1 Quinn Therm QR Pitched Roof Board is manufactured by blending together polyol and MDI in a continuous foaming process aided by a blowing agent, and sandwiched between two composite foil-facings. After formation, the boards are left to cure and are cut to size.

2.2 As part of the assessment and ongoing surveillance of product quality, the BBA has:

- agreed with the Certificate holder/manufacturer the quality control procedures and product testing to be undertaken
- assessed and agreed the quality control operated over batches of incoming materials
- monitored the production process and verified that it is in accordance with the documented process
- evaluated the process for management of nonconformities
- checked that equipment has been properly tested and calibrated
- undertaken to carry out the above measures on a regular basis through a surveillance process, to verify that the specifications and quality control operated by the manufacturer are being maintained.

2.3 The management system of Quinn Therm Ltd has been assessed and registered as meeting the requirements of BS EN ISO 9001 : 2008 by Certification Europe (Certificate 2500/262).

3 Delivery and site handling

3.1 The product is delivered to site in polythene-wrapped packs. Each pack of boards contains a label bearing the manufacturer's name, board dimensions and the BBA logo incorporating the number of this Certificate.

3.2 The product must be protected from prolonged exposure to sunlight, and stored dry, flat and raised above ground level (to avoid contact with ground moisture). Where possible, packs should be stored inside. If stored outside, the product should be under cover, or protected by opaque polythene sheeting.

3.3 The product is light and easy to handle and care should be exercised to avoid crushing the edges or corners. If damaged, the product should be discarded.

3.4 The product must not be exposed to open flame or other ignition sources, or solvents or other chemicals.

Assessment and Technical Investigations

The following is a summary of the assessment and technical investigations carried out on Quinn Therm QR Pitched Roof Board.

Design Considerations

4 Use

4.1 Quinn Therm QR Pitched Roof Board is suitable for use as insulation within tiled or slated pitched roofs, in conjunction with internal lining board, roof tile underlay, timber counter battens and tiling battens, in new and existing domestic or non-domestic buildings, and may be installed:

- above sloping rafters
- above and between sloping rafters
- between and below sloping rafters
- below horizontal ceiling joists (horizontal ceiling above a room in the roof)
- between and/or to the inner face of studs in dwarf walls and dormer cheeks.

4.2 Roofs should be designed and constructed in accordance with the relevant clauses of BS 5250 : 2011, BS 5534 : 2014, BS 8212 : 1995 and BS EN 1995-1-1 : 2004.

4.3 For optimum thermal performance, the product shall be installed with the correct orientation of its foil-facing. See section 14.3.

4.4 The product is not a structural component.

4.5 During installation, care should be exercised to ensure that the product is not subjected to any construction, or foot traffic, loads. Roof timbers of adequate strength should be used to support such loads.

4.6 It is essential that detailing and jointing of the boards achieves a convection-free envelope of high vapour resistance. Any gaps should be filled and/or taped. Ridges, abutments and penetrations should also be sealed. Flue pipes passing through the insulation should be suitably sleeved.

4.7 The provision of fire stops should be carried out in accordance with the requirements of the national Building Regulations.

5 Practicability of installation

The product is designed to be installed by a competent general builder, or a contractor, experienced with this type of product.

6 Thermal performance



6.1 Calculations of the thermal transmittance (U value) of specific roof constructions should be carried out in accordance with BS EN ISO 6946 : 2007 and BRE Report BR 443 : 2006, using the declared thermal conductivity (λ_D)* of $0.022 \text{ W}\cdot\text{m}^{-1}\cdot\text{K}^{-1}$ for the insulation, and a tested aged emissivity (ϵ_D) (to BS EN 15976 : 2011) of 0.06 for the unprinted foil-facing.

6.2 The U value of a completed roof will depend on the insulation thickness, and number and type of fixings, the roof structure and its internal finish. Calculated U values for example constructions in accordance with the national Building Regulations are given in Table 2.

Table 2 Roof U values — pitched roof

U value ($\text{W}\cdot\text{m}^{-2}\cdot\text{K}^{-1}$)	Over Rafters	Between Rafters	Between and Under Rafters
0.13	150	—	100 + 85
0.15	130	—	100 + 65
0.16	120	—	100 + 60
0.18	105	—	100 + 45
0.20	95	—	95 + 35
0.25	70	135 ^{*(1)}	80 + 25

(1) With additional 38 mm timber battens added beneath 150 mm rafters to maintain 50 mm vented cavity (138 mm maximum depth of insulation between rafters).

Junctions



6.3 Care must be taken in the overall design and construction of junctions with other elements and openings to minimise thermal bridges and air infiltration. Detailed guidance can be found in the documents supporting the national Building Regulations.

7 Condensation risk

Interstitial condensation



7.1 Roofs will adequately limit the risk of interstitial condensation when they are designed and constructed in accordance with BS 5250 : 2011 Annex H and the relevant guidance.

7.2 The risk of interstitial condensation will be minimal under normal conditions of use. The foil-facings have a water vapour resistance of $1000 \text{ MN}\cdot\text{s}\cdot\text{g}^{-1}$ and the insulation core has a water vapour resistivity of $300 \text{ MN}\cdot\text{s}\cdot\text{g}^{-1}\cdot\text{m}^{-1}$ and, when

installed with tightly-butted joints, filled/sealed gaps and joints, will provide a continuous convection-free envelope of high vapour resistance. Therefore, a suitable vapour-permeable (LR) roof tile underlay may be laid over the insulation boards without ventilated air space. When using a high resistance (type HR) underlay, the space below it must be ventilated in accordance with BS 5250 : 2011 Annex H.

7.3 Where the product is installed in a roof with either a horizontal or sloping ceiling (ie room-in-the-roof), a 'warm roof' space is created and ventilation should be designed in accordance with BS 5250 : 2011 Annex H. However, any insulation in a horizontal ceiling should be removed.

7.4 Where high humidity may be expected, a vapour control layer (VCL), such as 0.125 mm thickness polyethylene with sealed and lapped joints, should also be installed unless a condensation risk analysis in accordance with BS 5250 : 2011 shows that it is not necessary.

Surface condensation



7.5 Roofs will adequately limit the risk of surface condensation when the thermal transmittance (U value) does not exceed $0.35 \text{ W}\cdot\text{m}^{-2}\cdot\text{K}^{-1}$ at any point and the junctions with walls are designed in accordance with section 6.3 of this Certificate.



7.6 Roofs will adequately limit the risk of surface condensation when the thermal transmittance (U value) does not exceed $1.2 \text{ W}\cdot\text{m}^{-2}\cdot\text{K}^{-1}$ at any point. Guidance may be obtained from BS 5250 : 2011 Annex H. Further guidance may be obtained from BRE Report BR 262 : 2002 and section 6.3 of this Certificate.

8 Behaviour in relation to fire

8.1 The product has a reaction to fire classification* of Class F to BS EN 13501-1 : 2007 for 20 mm to 55 mm thicknesses and Class E for 60 mm to 200 mm thicknesses.

8.2 When installed between, under or over rafters, with an internal lining board securely fixed to timber (eg 12.5 mm thick plasterboard), the product will be contained between the element and internal lining board until one is destroyed. Therefore, the product will not contribute to the development stages of a fire until the lining is compromised.

8.3 Elements must incorporate cavity barriers at edges, around openings, at junctions with fire-resisting elements and in cavities in accordance with the relevant provisions of the national Building Regulations.

8.4 The use of the product will not affect the fire rating obtained by tiled or slated roofs when evaluated by assessment or test to BS 476-3 : 2004 or BS EN 13501-5 : 2005.

9 Strength

The product, when installed in accordance with the manufacturer's instructions and this Certificate, will resist the loads likely to be met during installation and in service.

10 Structural stability (over rafter application only)

10.1 Resistance to wind uplift will depend largely on the building geometry and its geographical location and should be calculated in accordance with BS EN 1991-1-3 : 2003 and its UK National Annex. Snow loadings should be calculated in accordance with BS EN 1991-1-3 : 2003 and its UK National Annex.

10.2 When calculating the fixing spacing required to resist the calculated loadings, the requirements of BS EN 1995-1-1 : 2004 and its National Annex should be followed where possible. Further guidance can be obtained from the Certificate holder. The Certificate holder and fixing manufacturer must advise on the use of the correct proprietary fixings and approved nails and fixing capacity in accordance with BS EN 1995-1-1 : 2004 and its UK National Annex.

11 Resistance to moisture

An effective roof tile underlay will protect the product from wind-driven snow or rain penetrating the tiling in service.

12 Maintenance

As the product is confined within the pitched roof by the overlay and has suitable durability (see section 13), maintenance is not required.

13 Durability



The product is durable, rot-proof and sufficiently stable to remain effective as an insulation for the life of the building.

Installation

14 General

14.1 Installation of Quinn Therm QR Pitched Roof Board must be in accordance with the relevant clauses of BS 5534 : 2014, and the manufacturer's instructions. Installation can be carried out in all conditions normal to roofing work.

14.2 The product is light to handle but some handling difficulties may be experienced in windy conditions. Since the product will not support the weight of operatives, appropriate care must be taken during installation and tiling.

14.3 The product has printed logos applied to the outer foil-facing on one side only. To ensure optimum thermal performance, these boards must be installed with the unprinted foil-face always facing the cavity side.

14.4 The product can be cut easily using a sharp knife or fine tooth saw. Care must be taken to prevent damage particularly to edges. Damaged boards should not be used. Small areas of damaged facing may be repaired with self-adhesive aluminium foil tape.

14.5 It is important to fill/seal gaps and joints in the insulation envelope, including at all service penetrations.

14.6 For installation of internal lining boards, see sections 15.21 and 15.22 of this Certificate.

15 Procedure


Insulation above rafters

15.1 A treated timber stop batten, the same thickness as the insulation board, is fixed to the rafters close to the eaves to provide a firm fixing point for the counter battens. The product is laid over the rafters, commencing at the stop batten. The product should be tightly butted and positioned in a staggered pattern, with all the joints running from eaves to ridge occurring over the rafters. The procedure is continued until the whole area is covered.

15.2 Any gaps must be sealed with flexible sealant or expanded foam. Large-headed clout nails can be used as a temporary securing measure until the counter battens are secured into place.

15.3 A vapour-permeable (LR) roofing underlay should be installed on top of the insulation, secured with counter battens, followed by tiling battens.

Figure 1 Typical Installation — Insulation above rafters




Insulation between and above rafters

15.4 The product is cut to fit tightly within the space between the rafters, and can be restrained using proprietary clips or timber sections.

15.5 The product is installed flush with the top of the rafters.

15.6 A second layer of insulation board is then fixed above the rafters, installed as described in 15.1 to 15.3.

Figure 2 Typical Installation — Insulation between and above rafters



Insulation between rafters

15.7 The product is cut to fit tightly within the space between the rafters and restrained using proprietary clips or timber battens, allowing sufficient depth for the insulation to sit flush with the underside of the rafters.

15.8 A ventilation gap of 50 mm must be maintained between the top of the insulation and roof tile underlay to minimise the risk of condensation, unless a vapour-permeable (LR) underlay is used.

15.9 When using a vapour-permeable (LR) roofing underlay on top of the rafters, the insulation can be installed full depth between the rafters ie flush with the top and bottom of the rafters. Counter battens are then installed over the underlay, followed by tiling battens.


15.10 When using a high resistance (HR) roofing underlay on the top of the rafters, the insulation should be installed part depth between the rafters ie flush with the bottom of the rafters and set to create a 50 mm void between the top of the insulation and the top of the rafter for ventilation. Tiling battens are applied over the roofing underlay.

Between and below rafters

15.11 If required, after installation between rafters as described in sections 15.9 or 15.10, a second layer of the product may be added below the rafters, running at right angles to the rafters and insulation fill, in a staggered pattern, and fixed accordingly.

15.12 The product should be butted tightly against itself to prevent gaps. Taping the joints with a self-adhesive aluminium foil tape provides an effective air permeability barrier. To achieve an adequate bond, the product should be clean and free from any contamination.

Figure 3 Typical Installation — Insulation between and below rafters



Horizontal ceiling above a room in the roof — below joists only

15.13 Mineral wool is packed between the ceiling joists, flush with the upper surface of the ceiling joist.

15.14 The product is temporarily fixed to the underside of the timber joists.

15.15 The line of the timber joists is marked on the boards to allow fixing of the plasterboard lining.

Dwarf walls and dormer cheeks — between studs

15.16 Timber stop battens or clips are fixed to the inner face of the studs, allowing sufficient depth for the insulation to sit flush with the inside of the studs. The product is cut to size and placed between the studs and held in place with clout nails.

Dwarf walls and dormer cheeks — between studs and lining

15.17 Timber stop battens or clips are fixed to the inner face of the studs, allowing sufficient depth for the insulation to sit flush with the inside of the studs. The product is cut to size and placed between the studs and held in place with clout nails.

15.18 A second layer of the product is temporarily fixed to the inner face of the timber studding.

15.19 The line of the timber studs is marked on the boards to allow fixing of the plasterboard.

15.20 The product should be butted tightly against itself to prevent gaps. Taping the joints with an acrylic adhesive foil tape provides an effective VCL and an air permeability barrier. To achieve an adequate bond, the boards should be clean and free from any contamination.

Finishing

15.21 Roof tiles or slates are installed in accordance with the relevant clauses of BS 5534 : 2003. When applying roof tiles or slates to a warm roof construction, the recommendations of the manufacturer should be followed.

15.22 A sealed polythene VCL with a minimum thickness of 0.125 mm with lapped and sealed joints is placed over the rafter, joist or stud face before applying the internal finishing plasterboard lining to BS EN 520 : 2004, fixed in accordance with BS 8212 : 1995.

Technical Investigations

16 Tests

Results of tests were assessed to determine:

- thermal conductivity
- dimensional stability
- flatness after one-sided wetting
- thickness.
- reaction to fire.

17 Investigations

17.1 An examination was made of data relating to:

- dimensional accuracy
- squareness
- density
- flatness
- compressive strength
- dimensional stability
- water vapour transmission.

17.2 A condensation risk analysis was carried out.

17.3 A series of U value calculations were carried out.

17.4 A calculation was undertaken to confirm the declared thermal conductivity.

17.5 The manufacturing process was examined, including the methods adopted for quality control, and details were obtained of the quality and composition of the materials used.

Bibliography

BS 476-3 : 2004 *Fire tests on building materials and structures — Classification and method of test for external fire exposure to roofs*

BS 5250 : 2011 *Code of practice for control of condensation in buildings*

BS 5534 : 2014 *Slating and tiling for pitched roofs and vertical cladding — Code of practice*

BS 8212 : 1995 *Code of practice for dry lining and partitioning using gypsum plasterboard*

BS EN 520 : 2004 *Gypsum plasterboards — Definitions, requirements and test methods*

BS EN 1991-1-3 : 2003 *Eurocode 1 : Actions on structures — General actions — Snow loads*

NA to BS EN 1991-1-3 : 2003 *UK National Annex to Eurocode 1 : Actions on structures — General actions — Snow loads*

BS EN 1995-1-1 : 2004 *Eurocode 5 : Design of timber structures — General — Common rules and rules for buildings*

NA to BS EN 1995-1-1 : 2004 *Eurocode 5 : Design of timber structures — General — Common rules and rules for buildings*

BS EN 13165 : 2012 *Thermal insulation products for buildings — Factory made rigid polyurethane foam (PU) products — Specification*

BS EN 13501-1 : 2007 *Fire classification of construction products and building elements — Classification using test data from reaction to fire tests*

BS EN 13501-5 : 2005 *Fire classification of construction products and building elements — Classification using data from external fire exposure to roof tests*

BS EN 15976 : 2011 *Flexible sheets for waterproofing — Determination of emissivity*

BS EN ISO 6946 : 2007 *Building components and building elements — Thermal resistance and thermal transmittance — Calculation method*

BS EN ISO 9001 : 2008 *Quality management systems — Requirements*

BRE Report (BR 262 : 2002) *Thermal insulation: avoiding risks*

BRE Report (BR 443 : 2006) *Conventions for U-value calculations*

18 Conditions

18.1 This Certificate:

- relates only to the product/system that is named and described on the front page
- is issued only to the company, firm, organisation or person named on the front page – no other company, firm, organisation or person may hold claim that this Certificate has been issued to them
- is valid only within the UK
- has to be read, considered and used as a whole document – it may be misleading and will be incomplete to be selective
- is copyright of the BBA
- is subject to English Law.

18.2 Publications, documents, specifications, legislation, regulations, standards and the like referenced in this Certificate are those that were current and/or deemed relevant by the BBA at the date of issue or reissue of this Certificate.

18.3 This Certificate will remain valid for an unlimited period provided that the product/system and its manufacture and/or fabrication, including all related and relevant parts and processes thereof:

- are maintained at or above the levels which have been assessed and found to be satisfactory by the BBA
- continue to be checked as and when deemed appropriate by the BBA under arrangements that it will determine
- are reviewed by the BBA as and when it considers appropriate.

18.4 The BBA has used due skill, care and diligence in preparing this Certificate, but no warranty is provided.

18.5 In issuing this Certificate the BBA is not responsible and is excluded from any liability to any company, firm, organisation or person, for any matters arising directly or indirectly from:

- the presence or absence of any patent, intellectual property or similar rights subsisting in the product/system or any other product/system
- the right of the Certificate holder to manufacture, supply, install, maintain or market the product/system
- actual installations of the product/system, including their nature, design, methods, performance, workmanship and maintenance
- any works and constructions in which the product/system is installed, including their nature, design, methods, performance, workmanship and maintenance
- any loss or damage, including personal injury, howsoever caused by the product/system, including its manufacture, supply, installation, use, maintenance and removal
- any claims by the manufacturer relating to CE marking.

18.6 Any information relating to the manufacture, supply, installation, use, maintenance and removal of this product/system which is contained or referred to in this Certificate is the minimum required to be met when the product/system is manufactured, supplied, installed, used, maintained and removed. It does not purport in any way to restate the requirements of the Health and Safety at Work etc. Act 1974, or of any other statutory, common law or other duty which may exist at the date of issue or reissue of this Certificate; nor is conformity with such information to be taken as satisfying the requirements of the 1974 Act or of any statutory, common law or other duty of care.